


Non-Rotating




POWERLIFT 35, 35L

- Very strong rotation - resistance
- High structural stability
- High breaking load
- Excellent resistance to deformation
- Suitable rope for high lifting Tower crane
- Excellent life time

Nominal Data		Minimum Breaking Load(Metric Ton)			Approx Weight Kg/m
mm	Inch	180Kg/mm ² (1770N/mm ²)	200Kg/mm ² (1960N/mm ²)	220Kg/mm ² (2160N/mm ²)	
14		13.7	16.3	17.9	0.87
14.3	9/16"	14.3	17.0	18.5	0.91
15		15.7	18.7	20.3	1.00
16	5/8"	17.9	21.3	23.0	1.14
17.5	11/16"	21.4	25.5	27.6	1.36
18		22.6	26.9	29.5	1.44
19	3/4"	25.2	30.0	32.6	1.60
20		28.0	33.3	36.1	1.78
21	13/16"	30.8	36.7	39.8	1.96
22		33.8	40.3	43.7	2.15
22.2	7/8"	34.5	41.1	44.6	2.19
24	15/16"	40.3	47.9	51.9	2.56

Nominal Data		Minimum Breaking Load(Metric Ton)			Approx Weight Kg/m
mm	Inch	180Kg/mm ² (1770N/mm ²)	200Kg/mm ² (1960N/mm ²)	220Kg/mm ² (2160N/mm ²)	
25		43.7	52.0	56.3	2.77
25.4	1"	45.1	53.7	58.2	2.86
26	1-1/16"	47.3	56.2	61.0	3.00
28		54.8	65.2	70.4	3.48
28.6	1-1/8"	57.2	68.0	73.5	3.63
30	1-3/16"	62.9	74.8	80.8	3.99
31.8	1-1/4"	70.7	84.1	90.8	4.49
32		71.6	85.2	92.0	4.55
34		80.8	96.1	103.8	5.13
35	1-3/8"	85.6	101.9	110.0	5.44
36		90.6	107.8	116.4	5.75
38		100.9	120.1	129.7	6.41

☐ Available upon request (Operation in poor condition is not recommendable)



POWERLIFT 19

- Rotation - resistance
- High structural stability
- High breaking load
- Excellent life time

Nominal Data		Minimum Breaking Load(Metric Ton)				Approx Weight Kg/m
mm	Inch	165Kg/mm ² (1620N/mm ²)	180Kg/mm ² (1770N/mm ²)	200Kg/mm ² (1960N/mm ²)	220Kg/mm ² (2160N/mm ²)	
6		2.2	2.4	2.6	2.8	0.15
6.53	1/4"	2.6	2.8	3.0	3.3	0.18
8	5/16"	3.8	4.2	4.5	5.0	0.27
9		4.9	5.3	5.7	6.3	0.34
9.53	3/8"	5.4	6.0	6.4	7.1	0.38
10		6.0	6.6	7.1	7.8	0.42
11.2	7/16"	7.5	8.2	8.9	9.8	0.52
12		8.6	9.4	10.2	11.2	0.60
12.7	1/2"	9.7	10.6	11.4	12.5	0.67
13		10.1	11.1	12.0	13.1	0.70
14		11.8	12.8	13.9	15.2	0.82
14.3	9/16"	12.3	13.4	14.5	15.9	0.85
15		13.5	14.8	15.9	17.5	0.94
16	5/8"	15.4	16.8	18.1	19.9	1.07
17.5	11/16"	18.4	20.1	21.7	23.8	1.28

Nominal Data		Minimum Breaking Load(Metric Ton)				Approx Weight Kg/m
mm	Inch	165Kg/mm ² (1620N/mm ²)	180Kg/mm ² (1770N/mm ²)	200Kg/mm ² (1960N/mm ²)	220Kg/mm ² (2160N/mm ²)	
18		19.4	21.2	23.0	25.2	1.35
19	3/4"	21.7	23.7	25.6	28.1	1.50
20		24.0	26.2	28.3	31.1	1.67
21	13/16"	26.5	28.9	31.2	34.3	1.84
22		29.0	31.7	34.3	37.6	2.02
22.2	7/8"	29.6	32.4	35.0	38.4	2.06
24	15/16"	34.6	37.8	40.8	44.8	2.40
25		37.5	41.0	44.3	48.6	2.60
25.4	1"	38.7	42.3	45.7	50.2	2.69
26	1-1/16"	40.6	44.3	47.9	52.6	2.82
28		47.0	51.4	55.5	-	3.27
28.6	1-1/8"	49.1	53.6	57.9	-	3.41
30	1-3/16"	54.0	59.0	63.8	-	3.75
31.8	1-1/4"	60.7	66.3	71.6	-	4.21
32		61.4	67.1	72.5	-	4.27